

## Powerful protection in stressful environments.

Our recyclable CustomKote® paperboard is strong and durable enough to stand up to even the most stressful environments throughout the supply chain. As versatile as it is tough, you can rely on CustomKote for a wide range of applications.

### Features

- Excellent strength properties for dry, refrigerated and frozen environments
- Can be converted with the kraft side out for a natural look
- Proprietary clay coating with a smooth and opaque surface

### Benefits

- Can maintain its integrity throughout the supply chain, offering optimal product protection
- Enables crisp, vibrant graphics
- Can help advance corporate sustainability goals
- Offers versatility for a wide range of applications including food, beauty and personal care, home and garden, and sporting goods

### Additional product information

#### Sustainability

- Made with up to 15% recycled fibre.
- Recyclable.
- 100% PEFC Certified - NQA-PEFC-COC-0332. Contact your Smurfit Westrock sales representative for certified fibre availability for this product.
- Certified to Chain of Custody Standards
  - SFI, PEFC/29-31-216
  - FSC C104002

#### Quality

- Manufactured in a Smurfit Westrock North American facility certified under ISO 9001, ensuring consistent quality management standards.

#### Environmental and Product Safety

- Notices under US California Proposition 65 and the EU REACH regulation are not required.
- Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

#### Food Contact

- Meets multiple national requirements for food contact packaging, e.g., US, Canada, Germany and the EU. Contact your sales representative for information on specific markets and end uses.
- ISEGA Certificate available.

### Applications

- Bakery
- Beauty and personal care
- Beverage
- Filter frames
- Food packaging
- Foodservice
- Home and garden
- Spirits
- Sporting goods

### Product classification

- Coated Natural Kraft™
- CNK® Paperboard
- Coated Unbleached Kraft

### Region

- EMEA (Europe, the Middle East and Africa)

## Grade availability (EMEA) and typical board properties

Grade availability										Units	Method	
Nominal basis weight	290	330	360	390	415	450	485	520	555	gsm	T-410	
Caliper (pts)	0.014	0.016	0.018	0.020	0.022	0.024	0.026	0.028	0.030	inches	T-411	
Thickness	356	406	457	508	559	610	660	711	762	microns	T-411	
Moisture content	6.6	6.6	6.6	6.6	6.6	6.6	6.6	6.6	6.6	percent	T-412	
ZDT	241	241	241	241	241	241	241	241	241	kPa	T-541	
<b>Stiffness</b>												
Taber 15°	MD	13.7	19.6	27.0	34.3	43.1	53.4	63.7	74.5	85.3	mNm	T-489
	CD	6.9	9.8	13.7	17.2	20.6	25.0	30.4	36.3	41.7	mNm	T-489
<b>Smoothness</b>												
Sheffield	100	100	115	140	145	145	165	165	165	SU	T-538	
<b>Coated side</b>												
GE Brightness	78	78	78	78	78	78	78	78	78	percent	T-452	
Parker Print	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	1.7	µm	T-555	
<b>Colour</b>												
Hunter	b	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	L-a-b	T-524	

Values are subject to change without notice.

For more information, please contact your Smurfit Westrock representative or visit our website at [smurfitwestrock.com](https://www.smurfitwestrock.com).

The information contained in this Product Guide is accurate to the best of Smurfit Westrock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. Smurfit Westrock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

©2026 Smurfit Westrock and/or its affiliates. Smurfit Westrock and the Smurfit Westrock logo are trademarks owned by Smurfit Westrock and/or its affiliates. All rights reserved.

